

Accurate polymorphous description of the paramagnetic phases in MnBi_2Te_4

Yufei Zhao^a, Qiushi Yao^a, Pengfei Liu^a, Qihang Liu^{a,b,c,*}

^a Department of Physics, Southern University of Science and Technology, Shenzhen 518055, China

^b Guangdong Provincial Key Laboratory for Computational Science and Material Design, Southern University of Science and Technology, Shenzhen 518055, China

^c Shenzhen Key Laboratory of Advanced Quantum Functional Materials and Devices, Southern University of Science and Technology, Shenzhen 518055, China

ARTICLE INFO

Keywords:

Topological materials
Paramagnetic phase
Density-functional theory
Surface
Antiferromagnetism
Magnetic insulator
Thin films
Special quasirandom structures
Phase transition

ABSTRACT

Temperature-driven phase transition is a long-standing frontier in material science, among which the most common phenomenon is the transition from a low-temperature magnetic-ordered phase to a high-temperature paramagnetic phase. A paramount question is if such a paramagnetic phase of the “correlated solids” can be well described by single-particle band theory to facilitate the experimental observations. In this work, we investigate the electronic properties of the paramagnetic phase by the static density functional theory *via* two different approaches, namely monomorphous description and polymorphous description. In the conventional monomorphous description, the local spin moments are naively forced to be zero. By contrast, the polymorphous description based on a large enough supercell with disordered distributed local moments is able to count in the effects of distinct local environments, providing a more reliable paramagnetic electronic structure to simulate realistic materials. From a comparison of total energies, symmetries, and band structures, we demonstrate the necessity for a proper treatment of paramagnetic phases, taking MnBi_2Te_4 as an example. Our work provides a theoretical perspective on the evolution of electronic structures through magnetic order-disorder phase transitions in emergent topological magnets.

1. Introduction

Time-reversal (\mathcal{T}) symmetry is known to play a primary role in the characteristics of topological phases of matter [1,2]. Its presence or absence is a bedrock for the classification and achievement of emergent quantum phenomena, such as quantum spin Hall (QSH) effect in a \mathcal{T} -preserved topological insulator [3] and quantum anomalous Hall (QAH) effect in a \mathcal{T} -broken Chern insulator [4]. In the past few years, experiment and theory have established elegant consistency in \mathcal{T} -broken systems and unearthed a series of ordered magnetic topological insulators and Weyl semimetals with the long-range magnetic order [5–14]. However, a long-standing problem in density-functional theory (DFT) is how to deal with paramagnetic (PM) phases with disordered distributed local moments, where \mathcal{T} is globally preserved due to macroscopically zero net spin moments but locally broken around the magnetic ions [15].

Before reviewing this problem, it should be noted that the evolution of the electronic band structure with temperature provides direct evidence of magnetism-induced topological phase transitions. For instance, the surface gap of a magnetic topological insulator is the

prerequisite for realizing the QAH effect and axion response [16]. Such a gap originates from magnetism (rather than other effects such as Coulomb scattering [17]) only if it disappears with temperature T past the critical temperatures T_C or T_N [8]. Another expected possible scenario is in magnetic Weyl semimetal, whether two Weyl points merge to a Dirac point or are gapped to an insulator [18]. Observing these electronic fine changes cannot be done by solely tracing any “kinks” in other order parameters, such as heat capacity $C(T)$ or susceptibility $\chi(T)$.

Conventionally, the PM phase from first-principles calculations is done by simply forcing the local moment of each magnetic atom (e.g., transition-metal atom) to be homogeneously zero for a macroscopic statistical behavior, namely a nonmagnetic (NM) monomorphous description [6,19–22]. In other words, the magnetic cations are symmetry-equivalent and share an identical local environment. Although such an approximation yields reasonable results in some scenarios, it usually leads to severe discrepancies with the physical reality and experiments. One may note that a broad range of Mott insulators and perovskites with 3d electrons have been reported to maintain their bandgap in both low- T and high- T phases, but however, these

* Corresponding author at: Department of Physics, Southern University of Science and Technology, Shenzhen 518055, China.

E-mail address: liuqh@sustech.edu.cn (Q. Liu).

compounds exhibit false-positive metallic states under the NM monomorphous calculations [23–27]. As a result, the mean-field DFT was once claimed to be insufficient for describing the correlated PM phases.

Indeed, when the local moments of the magnetic atoms are randomly aligned at $T > T_C$, the resultant PM phase has an ensemble-averaged property $\langle P(S^i) \rangle$ (e.g., band structure) from numerous random magnetic configurations S^i . By contrast, the monomorphous approach, i.e. the NM model within a single minimal primitive cell, yields a property $P(\langle S^i \rangle)$ of artificially averaged magnetic structure $\langle S^i \rangle$ at each atomic site [26,15,28]. Consequently, spurious \mathcal{F} symmetry (both globally and locally) and crystalline symmetries lead to artificial results such as partial filling of bands and thus problematic predictions of the wavefunctions as well as the topological properties.

This article attempts to answer a simple yet undeniable question: How to identify the magnetic order–disorder phase transition directly from DFT-calculated band structures? We address it by applying the *state-of-the-art* polymorphous description to offer a prediction for the bulk and thin films. The rest of the paper is organized as follows. Section 2 provides the methodology adopted and computational details. In Section 3, the intrinsic magnetic topological insulator MnBi_2Te_4 is taken as a typical example. Through the polymorphous calculations, we find exclusive advantages of this method in describing the band structure and total energy, which is well consistent with the previous experiments. Our results establish an important routine for capturing the transition signals, in order to compare with angle-resolved photoemission spectroscopy (ARPES) and scanning tunneling microscope (STM) measurements.

2. Methods

Our DFT calculations are carried out by using the projector augmented-wave (PAW) method, implemented in Vienna *ab-initio* Simulation Package (VASP) [29–31]. The Perdew-Burke-Ernzerhof (PBE) type exchange-correlation functional in the generalized gradient approximation (GGA) [32] is adapted to take into account exchange and correlation contributions to the Hamiltonian of the electron-electron system. Since the on-site Coulomb interactions among electrons on Mn-3d are strong, we have taken $U = 5.0$ eV as a parameter in the GGA+ U calculations [33]. We apply the DFT-D3 approach [34] to describe the van der Waals interactions. To account for the effect of fluctuated magnetic moments on the total energy, the coordinates of the atoms are optimized (only for the bulk). Energy cost as a function of magnetic moment is performed via the constrained density functional theory (CDFT) [35]. In order to obtain an intuitive electronic spectrum rather than confused heavily folded bands, we apply a rigorous band unfolding [36,37] to obtain an effective band structure (EBS) in a primitive Brillouin zone,

$$P_{\vec{k}_m}(\vec{k}_i) = \sum_n |(\vec{k}_m | \vec{k}_i)_n|^2, \quad (1)$$

where $|\vec{k}_m\rangle$ and $|\vec{k}_n\rangle$ are the eigenvectors of the supercell and primitive cell. $|\vec{k}_m\rangle$ can be expressed as a linear combination of primitive cell eigenvectors $|\vec{k}_n\rangle$. The spectral weight is given by

$$A(\vec{k}_i, E) = \sum_m P_{\vec{k}_m}(\vec{k}_i) \delta(E_m - E). \quad (2)$$

This process is implemented in the open-source code BANDUP [38,39].

We next introduce how to polymorphously simulate the disordered PM phase by applying the “special quasirandom structures” (SQSs) method [40]. Instead of averaging the band structures of many PM snapshot configurations $\{S^i\}$, which belongs to another form of polymorphous description but is clumsy and inefficient, we construct a single but large enough supercell that takes into account the individual local moments as well as the local disordered effects. It provides more reliable results than the ensemble average along many small random supercells. From statistical mechanics, the guidelines for picking the desired supercell are as follows.

2.1. Multisite correlation function

We first define a configuration S^i represented by a vector of occupation variables S_j^i , indicating which type of atom sits on lattice site j . In a multi-component system (e.g. alloy), M_j distinct chemical species can be assigned to occupy site j (denoted as $S_j^i = 0, \dots, M_j - 1$ due to its chemical composition). In most cases, the PM phase can be approximately treated as a binary alloy with two species: spin-up and spin-down. The reasons will be clarified later. We also need to define the “cluster” $\alpha^{\kappa, \xi}$ to characterize the κ -order arrangement of ξ th-nearest neighbor atoms, e.g. points α^1 , lines α^2 , triangles α^3 . For simplicity, ξ is omitted hereafter.

For a given configuration S , the multisite correlation function of a specific cluster α^{κ} is given by

$$\Gamma_{\alpha^{\kappa}}(S) = \prod_i \gamma_{\alpha^{\kappa}}(S_i). \quad (3)$$

In a binary alloy, a common choice of γ is $\gamma(0) = +1$ and $\gamma(1) = -1$. If we only consider $\kappa = 2$, it is the Ising model.

The correlation of the whole system is expressed as

$$\rho(\sigma) = \sum_{\alpha} D_{\alpha} m_{\alpha} \langle \Gamma_{\alpha'}(\sigma) \rangle_{\alpha^{\kappa}}, \quad (4)$$

where $\langle \Gamma_{\alpha'}(\sigma) \rangle_{\alpha^{\kappa}}$ sums over all the clusters α' which are symmetry equivalent to α^{κ} . m_{α} is the number of clusters α' . D_{α} is cluster expansion coefficients or cluster interaction potential. In the fully disordered PM phase with complete stochasticity, the correlation function is zero $\rho_{\alpha}(S^*) = 0$. To search for a supercell with a minimum correlation approaching $\rho_{\alpha}(S^*)$, we apply a Monte-Carlo method MCSQS implemented in Alloy Theoretic Automated Toolkit (ATAT) [41,42]. In this paper, the cutoff radii ξ of pair correlation ($\kappa = 2$) and triplet correlation ($\kappa = 3$) clusters are set between the second and third nearest neighbors.

2.2. Spin orientation

In the language of the classical Heisenberg model, at low temperatures, the magnetic moments interact with each other through (direct or super-) exchange interaction and tend to align parallel (ferromagnetic, FM) or antiparallel (antiferromagnetic, AFM) to reach the lower-energy ground state, expressed as [22]

$$\hat{H} = - \sum_{i,j} J_{ij} \sigma_i \sigma_j = - \sum_{\alpha} J_{\alpha} n_{\alpha} \langle \Phi_{\alpha} \rangle \quad (5)$$

where $\langle \Phi_{\alpha} \rangle = \frac{1}{N} \sum_{i,j \in \alpha} \sigma_i \sigma_j$ is the average spin-spin correlation of a given type of cluster α . J_{α} and n_{α} denote the coupling constant and the number of atoms. Consider a one-dimensional Ising model, the energies of the FM and AFM phases satisfy $E_{\text{FM}} = -E_{\text{AFM}} = -\sum_{\alpha} J_{\alpha}$. Because the averaged correlation function should fulfill $\langle \Phi_{\alpha} \rangle = 0$, $\forall \alpha$ in the disordered PM phase, $E_{\text{PM}} = 0$ is consistent with the requirement 2.1.

$\langle \Phi_{\alpha} \rangle = 0$ is quite helpful for making an approximation. Although the magnetic moments are 360° randomly aligned in real PM phases, we can still assume collinear spin configurations in calculations, as long as the parallel and antiparallel interactions are canceled when summing over clusters. The choice of the easy axis depends on the crystalline symmetries and may require testing. For example, van der Waals magnets usually exhibit large magnetic anisotropy energy (MAE), so their spin moment orientations can be initially set along the easy axis, and the amplitudes are free to evolve during the relaxation (flipping disallowed). But in certain scenarios (e.g. Mn_3Sn has a noncollinear but coplanar order [43]), we can adopt three (or more) in-plane directions as input to generate SQSs.

2.3. Central limit theorem (CLT)

A basic intuitive understanding behind the PM phase is that there could exist multiple local environments rather than a single environment (e.g. a cation can be surrounded by n^{\uparrow} spin-up ions plus n^{\downarrow} spin-




Fig. 1. The spin configuration and corresponding projected local density of states (PDOS) in MnBi_2Te_4 . (a)–(d) Upper panel: The weight of local spin configuration $F(n^{\uparrow\downarrow})$ in different spin configurations. (a) All the metal sites are identical for zero spins. (b) and (d) The spins of nearest neighbor cations in a layer, keep the same direction in the FM and A-type AFM phases ($n^{\uparrow\downarrow} = 0$ everywhere). (c) Distribution of the weights of local spin configurations in the PM supercell modeled by the 224-atom SQS shown in the inset (only the Manganese sites are shown). The bars describe the percentage of nearby opposite-spin sites when the central atom is spin-up (green) and spin-down (coral). (e)–(j) Lower panel: The d -orbitals PDOS of the manganese atom in the upper panel, respectively. (e) The NM model with a single atom in a unit cell induces a metallic gapless phase. (g)–(i) In the PM-SQS structure, the magnitude of moments in different local environments varies in a small range, and there is no accidental band gap closure for each individual atom. The inset shows the central atom's environment corresponding to $n^{\uparrow} = 5, 3, 2$ ($n^{\downarrow} = 1, 3, 4$). (f) and (j) FM and AFM motifs.

down ions, but $n^{\uparrow\downarrow}$ can differ at different sites). If we draw out a fixed-size supercell sample i randomly from a real PM phase and count the number of cations that are surrounded by ($n^{\uparrow\downarrow} = 0, 1, 2, 3, \dots$), we will have a distribution $F_i(n^{\uparrow\downarrow})$, representing the probability of finding an ion with $n^{\uparrow\downarrow}$. Repeating this independent and identically distributed (*i.i.d.*) process, we can have

$$\lim_{m \rightarrow \infty} \frac{1}{m} \sum_i^m F_i(n^{\uparrow\downarrow}) \rightarrow \mathcal{N}(\mu, \sigma^2/\sqrt{m}) \quad (6)$$

where the right side $\mathcal{N}(\mu, \sigma^2/\sqrt{m})$ is a normal distribution with the mean value $\mu = 0.5$. The finite variance of the real PM phase is set as σ^2 . In density functional theory, it is inevitable to introduce spurious spatial correlations by periodic structures, but CLT hints at an underlying principle that, the supercell with a normal distribution of $F(n^{\uparrow\downarrow})$ is optimal by technically minimizing the periodic errors. An example will be given in the next section (Fig. 1).

3. Results

In this section, we will employ a comparative study with different descriptions on MnBi_2Te_4 , which has received much attention recently [7,8,11,12,16,28]. This is the simplest example of a false-positive metal under the NM monomorphous method, enforced by an odd number of electrons within a unit cell and Kramers spin degeneracy.

As shown in Fig. 2(a), MnBi_2Te_4 crystalized in a van der Waals structure (space group $R\bar{3}m$) with a MnTe layer sandwiched by a quintuple layer (QL) Bi_2Te_3 , forming a septuple layer (SL). At low temperatures, MnBi_2Te_4 exhibits an AFM ground state, where spin moments in each SL are FM coupled and point out of planes. With spin-orbit coupling effect induced band inversion, the system is a \mathbb{Z}_2 AFM TI with gapped (001) surface states. In the two-dimensional thin films, the system is predicted to show alternating behaviors between the QAH (odd number of SLs) and axion insulator states (even number of SLs) [11]. However, the (001) surface states, which should be gapped by




Fig. 2. (a) Crystal structure of Bi₂Te₃ and MnBi₂Te₄ with an A-type AFM configuration. (b)–(d) Band dispersions of the (b) NM, (c) FM, and (d) AFM configurations. For the calculations of NM and FM phases, we use a single SL which causes double Brillouin zone length along Γ –Z. (e) The spectral functions of the PM phase by the polymorphous description with randomly distributed local moments. The spin-orbit coupling is included. (f) Total energy as a function of constrained local moments with an AFM configuration. A polynomial function is used to fit the total energy evolution.

magnetism, is experimentally observed to be gapless in the low- T AFM phase. This unresolved issue hinders the observation of the AFM-PM phase transitions.

In the high- T PM phase, MnBi₂Te₄ is expected to share many similarities as Bi₂Te₃. A naive but intuitive physical picture is as follows. Three-dimensional MnBi₂Te₄ will restore to a \mathcal{T} -preserved Z_2 TI with the gapless (001) surface states. In the thin film, a low- T QAH insulator is expected to be a QSH insulator or a trivial insulator in the high- T limit [44]. Luckily, ARPES measurement found the temperature-dependent transition signal, albeit rather less salient. The (001) surface states kept gapless in both the AFM and PM phases, and the bulk gap was unchanged [7]. However, it was clearly shown that the two conduction bulk bands merged into one band at some specific k path.

3.1. Bulk

The NM monomorphous approach, *i.e.*, the magnetic moment of Mn is set to zero within a primitive cell, is first considered to obtain the PM electronic structure of MnBi₂Te₄ (Fig. 1(a,e)). The unit cell consists of one SL that contains a single Mn atom. Guaranteed by space-time \mathcal{PT} symmetry, each energy band is at least double-degenerate (Fig. 2(b)). Note that a single Mn atom has five 3d electrons, so the total number of electrons within a primitive cell is odd. This indicates that the Fermi level must cut through at least one band, rendering a symmetry-enforced semimetal. Such a semimetal phase cannot be avoided by simply doubling the primitive cell, because it would fold each band at the boundary of the reduced Brillouin zone (BZ) rather than open a gap (Appendix Fig. A1(a)). Additionally, even if inversion symmetry is broken, it still exhibits a semimetal for Kramers degeneracy at time-reversal invariant wavevectors. Therefore, the oversimplified NM monomorphous model fails to predict the correct PM electronic structure of MnBi₂Te₄ due to the spurious high symmetry.

In the earlier DFT studies [45], the PM phase has also been naively treated as an AFM or FM phase (since the PM phase is composed of numerous microscopic AFM and FM configurations), which breaks not only the local \mathcal{T} symmetry but also the global \mathcal{T} symmetry. From the viewpoint of the distribution of spin configurations $F(n^{1/4})$ (the nearest neighbor shell), they could also be classified as monomorphous

descriptions for identical local environments. The nearest neighbor sites of all cations have the maximum spin-similarity, *i.e.*, $F(n^{1/4} = 0) = 1$ that disobeys CLT. While the false-positive metallic prediction is avoided under the AFM/FM configuration (Fig. 1(f,j)), some characteristics of the band structure are significantly different from those in the real PM phase, as we discuss next.

In the polymorphous framework, the PM band structure can be accommodated by building a $4 \times 4 \times 2$ SQS supercell (224 atoms), where local moments are randomly distributed (inset of Fig. 1(c)). The distribution of spin configurations $F(n^{1/4})$ (the nearest neighbor shell) satisfies CLT. Strictly speaking, all the original space group symmetries cannot survive. We also check that any unnecessary microscopic translational symmetry imposed by the supercell is avoided. In Fig. 1(g–i), each individual Mn²⁺ motif provides a finite band gap, rendering an overall bulk insulating phase. This is the most significant improvement compared to the NM monomorphous approach, consistent with ARPES measurements.

Fig. 2(e) shows the DFT-calculated spectral functions in the SQS, which are unfolded into the BZ of a $1 \times 1 \times 2$ cell in order to directly compare with the AFM bandstructure (Fig. 2(d)). The fuzziness of the spectral density in the long-wave vector region reflects the degree of retention of crystalline symmetry. At a glance of the dispersion and gap, the energy band looks very similar to that of the AFM ground state. The energy gap size is nearly the same at Γ (~ 0.18 eV). Since ARPES did not observe any band gap closing and reopening, one may ask if this system is still topologically nontrivial. Although in this case any symmetry-based indicators cannot be defined, band inversion is a rough way to address this question. In Appendix Fig. A2, we show the valence and conduction band weights (p orbitals of Bi and Te) at Γ are also inverted in the PM phase. Thus, the PM phase of MnBi₂Te₄ belongs to a globally \mathcal{T} -preserved “topological insulator” [7].

The evidence of the transition from the low- T AFM to high- T PM is reported to be two conduction bands merging at Z (0,0,0.5) [7]. This merging effect leads to a four-fold degeneracy, which is captured by our polymorphous calculations. The reason behind it is physically insightful. The PM-SQS can be regarded as a composition of the amount of the AFM and FM $1 \times 1 \times 2$ unit cells. However, in the AFM and FM phases, no such nonsymmorphic symmetry exists to protect band crossings at Z (Fig. 2(c,d)). In the mesoscopic scale of the PM phase, the translation, rotation, and \mathcal{T}

symmetries are recovered, but ARPES still detects the $1 \times 1 \times 2$ cell because of the presence of the local moments. Hence, this band merging phenomenon originates from the band folding effect at the BZ boundary when the system turns to the PM phase.

It is also known that the calculated energy difference reflects the stability of the phase or magnetic interactions [46]. The energy of the PM-SQS is only 4.83 meV/Mn higher than that of the AFM ground state and 2.48 meV/Mn higher than that of the FM phase. To some extent, it corresponds to a low Néel temperature ($T_N \approx 25$ K). In sharp contrast, the total energy of the NM monomorphous phase (4.5 eV/Mn) is around 1000 times higher than that of the polymorphous one, which apparently deviates from physical reality. The inevitable omission of the Zeeman splitting of Mn atoms leads to such a huge difference, revealed by a CDFT calculation (Fig. 2(f)). When decreasing the magnitude of local moments under the AFM configuration, the total energy increases gradually. A jump occurs at $|s| = 0 \mu_B$ (NM case) because $\mathcal{P}\mathcal{T}$ symmetry-enforced half-filling further lifts the band to Fermi level. To sum up, our results indicate the validity of the PM-SQS configurations when describing bulk states.

3.2. Thin film

Next we focus on the thin films of MnBi_2Te_4 . For each structure considered in Fig. 3, we build a 4×4 SQS and unfold it back to the unit cell for simulating the PM phase. According to the Dirac equation, magnetization-induced \mathcal{T} -broken mass term will open a gap. However, the hybridization between top and bottom surfaces is also capable of gap opening. The polymorphous view is helpful in diagnosing the gap-opening mechanism.

On the other hand, when increasing the number of QLs/SLs, in Bi_2Te_3 , there exists an oscillation behavior between the trivial insulator and the QSH insulator [44,47]; in MnBi_2Te_4 , there exists an oscillation behavior between the axion insulator and the QAH insulator [11]. Although these terminologies are ill-defined in the PM phase, the polymorphous band structure can provide a basic picture of these properties.

From 1 SL to 3 SLs, the band structures of the AFM and PM phases are shown in Fig. 3(a–c, e–g). In 1 SL, the finite-size effect overwhelms the magnetization, so both phases show a large gap of around 0.4 eV. Upon increasing thickness up to 2 SLs, the AFM order is built with $\mathcal{P}\mathcal{T}$ symmetry.

With less hybridization, two-SL- MnBi_2Te_4 yields an axion insulator state with zero Hall plateau [11]. In comparison, the general energy spectra of the PM phase differ from those of the AFM phase with a much smaller energy gap of 32 meV. In 3 SLs, the AFM phase shows the QAH effect with a 74 meV gap, while the PM phase shows a gap of nearly 9 meV. Starting from 2 SLs, we could expect that the band gap of the PM phase keeps decreasing but without vanishing, analogous to its NM counterpart [44].

Note that MnBi_2Te_4 is a vdW compound, which enables a series of assembling structures with Bi_2Te_3 . Thus, we also investigate an SL-QL-QL thin film. In the ground state (Fig. 3(d)), the previous studies have shown via the layer projection of the wave function that the energy gap at Γ at $E - E_F = 0.02$ eV, 0 eV, and -0.1 eV have different physical origins [48–50]. To be concrete, the gap at 0.02 eV [between the lowest conduction band and the second lowest conduction band] arises from the bottom SL and is associated with the magnetic exchange effect that breaks \mathcal{T} symmetry and lifts the degeneracy; the gap at 0 eV is caused by the finite size effect. When the slab is thick enough, the hybridization between the top and bottom surface states is negligible, and the gap will vanish; the energy bands near -0.1 eV [the first two highest conduction bands] are dominant by the top NM QL, which approximately retains \mathcal{T} symmetry because of the vanishingly small proximity effect. While the inversion symmetry is broken, this gapless Dirac point is still permitted but buried in the bulk valence bands. Hence, when the system turns to the PM phase [Fig. 3(h)], we find that only the gap at 0.02 eV closes while the latter two are essentially irrelevant to the magnetization, so they keep gapless/gapped. Our results reflect how the magnetic disorder restores the global \mathcal{T} symmetry and then affects the gap.

4. Discussion and conclusion

So far, we have analyzed the insulating system where each unit cell contains an odd number of electrons. One may ask if such a false-positive metallic prediction can be avoided in a system with an even number of electrons, so that the low-energy bands near the Fermi surface are guaranteed to be correct by the monomorphous description. It is accidentally true except in cases when crystalline symmetry plays a role. When the space group has a nonsymmorphic symmetry to




Fig. 3. (a–d) Calculated band structures of the thin film 1SL, 2SL, 3SL, and SL-2QL, respectively. The AFM ground state is assumed. The 3SL is a QAH insulator. (e–h) Band structures in the PM phase. Spectral weights are shown as the size of blue dots.

accommodate the four-fold degeneracy, the system with $4n+2$ electrons is again inevitably in a metallic state under the monomorphous description.

In summary, we comprehensively investigated the PM electronic structure of bulk (3D) and thin films (2D) of topological insulators, exemplified by MnBi_2Te_4 . First, we found a band merging effect at the BZ boundary with negligible change in the bulk gap. Second, the surface gap opened by magnetization will vanish in the PM configuration while the hybridization gap does not change. It is worth noting that an open question regarding 1D edge states is left here, which may provide ingredients for the study of topological Anderson insulators [51].

In the framework of single-particle mean-field DFT, performing the calculations with oversimplified approximation usually leads to unrealistic predictions, especially when the local disorder effect needs to be considered. In magnetic semiconductors where the local moments survive and distribute disorderly, a polymorphous description is required. Such an approach takes into account the otherwise neglected local symmetry breaking, as well as the correct exchange interaction. Our work provides a guiding principle to analyze the underlying physical properties of the PM phases, which will facilitate the investigation of the magnetic phase transition and topological magnets.

CRediT authorship contribution statement

Pengfei Liu: Methodology, Investigation, Formal analysis. **Qihang Liu:** Writing – review & editing, Supervision, Investigation, Formal

Appendix A. Convergence test of the supercell size

To rule out other possibilities of the band spectra, we also implement the calculations under different sizes of supercells with randomly distributed spin moments. There are three aspects to judge the convergence: band gap, dispersion, and degeneracy at high symmetry points. As shown in Fig. A1(a), the energy bands under the NM monomorphous description are double-degenerate at the Brillouin zone boundary (Z and L). In

analysis, Conceptualization. **Yufei Zhao:** Writing – original draft, Visualization, Validation, Methodology, Investigation, Formal analysis. **Qiushi Yao:** Methodology, Investigation, Formal analysis.

Data availability

Data will be made available on request.

Declaration of Competing Interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

Acknowledgments

Y. Zhao thanks discussion with Shulong Yang and Binghai Yan. This work was supported by the National Key R&D Program of China (Grant nos. 2020YFA0308900 and 2019YFA0704900), Guangdong Provincial Key Laboratory for Computational Science and Material Design (Grant no. 2019B030301001), Shenzhen Science and Technology Program (Grant no. RCJC20221008092722009), the Science, Technology and Innovation Commission of Shenzhen Municipality (Grant no. ZDSYS20190902092905285) and Center for Computational Science and Engineering of Southern University of Science and Technology.




Fig. A1. (a) Band structure under the monomorphous description. (b) Band structures under the polymorphous description by different size supercells, unfolded to a $1 \times 1 \times 2$ cell.




Fig. A2. Projected energy spectrum (Bi-*p* and Te-*p* orbitals) in the AFM phase (left) and PM phase (right). An inverted band order observed at Γ indicates a “PM topological insulator”.

principle, it can be used to judge the convergence of the supercell since two descriptions exhibit the same global symmetries. In Fig. A1(b), the band dispersion and unvanishing gap obtained from other supercell sizes are close to the $4 \times 4 \times 2$ one (Fig. 2(e)). The band degeneracy at *Z* point is quite robust, but the energy near *F* and *L* depends on the choice of the supercell.

To be concrete, while the $2 \times 1 \times 2$ cell accidentally achieves the degeneracy at *L*, the $2 \times 2 \times 2$ and $2 \times 2 \times 4$ cells fail to show that. Besides, the bands near *F* are evident to show the importance of the supercell size on the *ab* plane. Among them, only the $2 \times 3 \times 2$ and $4 \times 4 \times 2$ supercells are satisfactory for the dispersion near the *F* point.

References

- [1] M.Z. Hasan, C.L. Kane, Colloquium: topological insulators, *Rev. Mod. Phys.* 82 (2010) 3045.
- [2] X.-L. Qi, S.-C. Zhang, Topological insulators and superconductors, *Rev. Mod. Phys.* 83 (2011) 1057.
- [3] B.A. Bernevig, T.L. Hughes, S.-C. Zhang, Quantum spin hall effect and topological phase transition in *hgte* quantum wells, *Science* 314 (2006) 1757.
- [4] F.D.M. Haldane, Model for a quantum hall effect without landau levels: condensed-matter realization of the “parity anomaly”, *Phys. Rev. Lett.* 61 (1988) 2015.
- [5] C.-Z. Chang, J. Zhang, X. Feng, J. Shen, Z. Zhang, M. Guo, K. Li, Y. Ou, P. Wei, L.-L. Wang, et al., Experimental observation of the quantum anomalous Hall effect in a magnetic topological insulator, *Science* 340 (2013) 167.
- [6] H. Li, S.-Y. Gao, S.-F. Duan, Y.-F. Xu, K.-J. Zhu, S.-J. Tian, J.-C. Gao, W.-H. Fan, Z.-C. Rao, J.-R. Huang, et al., Dirac surface states in intrinsic magnetic topological insulators EuSn 2 as 2 and MnBi 2 n Te 3 n + 1, *Phys. Rev. X* 9 (2019) 041039.
- [7] Y.J. Chen, L.X. Xu, J.H. Li, Y.W. Li, H.Y. Wang, C.F. Zhang, H. Li, Y. Wu, A.J. Liang, C. Chen, S.W. Jung, C. Cacho, Y.H. Mao, S. Liu, M.X. Wang, Y.F. Guo, Y. Xu, Z.K. Liu, L.X. Yang, Y.L. Chen, Topological electronic structure and its temperature evolution in antiferromagnetic topological insulator MnBi_2Te_4 , *Phys. Rev. X* 9 (2019) 041040.
- [8] R. Lu, H. Sun, S. Kumar, Y. Wang, M. Gu, M. Zeng, Y.-J. Hao, J. Li, J. Shao, X.-M. Ma, Z. Hao, K. Zhang, W. Mansuer, J. Mei, Y. Zhao, C. Liu, K. Deng, W. Huang, B. Shen, K. Shimada, E.F. Schwiery, C. Liu, Q. Liu, C. Chen, Half-magnetic topological insulator with magnetization-induced dirac gap at a selected surface, *Phys. Rev. X* 11 (2021) 011039.
- [9] D.F. Liu, A.J. Liang, E.K. Liu, Q.N. Xu, Y.W. Li, C. Chen, D. Pei, W.J. Shi, S.K. Mo, P. Dudin, T. Kim, C. Cacho, G. Li, Y. Sun, L.X. Yang, Z.K. Liu, S.S.P. Parkin, C. Felser, Y.L. Chen, Magnetic weyl semimetal phase in a Kagomé crystal, *Science* 365 (2019) 1282.
- [10] C. Liu, Y. Wang, H. Li, Y. Wu, Y. Li, J. Li, K. He, Y. Xu, J. Zhang, Y. Wang, Robust axion insulator and Chern insulator phases in a two-dimensional antiferromagnetic topological insulator, *Nat. Mater.* 19 (2020) 522.
- [11] M.M. Otrokov, I.P. Rusinov, M. Blanco-Rey, M. Hoffmann, A.Y. Vyazovskaya, S.V. Eremeev, A. Ernst, P.M. Echenique, A. Arnau, E.V. Chulkov, Unique thickness-dependent properties of the van der Waals interlayer antiferromagnet MnBi_2Te_4 films, *Phys. Rev. Lett.* 122 (2019) 107202.
- [12] X.-M. Ma, Y. Zhao, K. Zhang, S. Kumar, R. Lu, J. Li, Q. Yao, J. Shao, F. Hou, X. Wu, M. Zeng, Y.-J. Hao, Z. Hao, Y. Wang, X.-R. Liu, H. Shen, H. Sun, J. Mei, K. Miyamoto, T. Okuda, M. Arita, E.F. Schwiery, K. Shimada, K. Deng, C. Liu, J. Lin, Y. Zhao, C. Chen, Q. Liu, C. Liu, Realization of a tunable surface dirac gap in Sb-doped MnBi_2Te_4 , *Phys. Rev. B* 103 (2021) L121112.
- [13] W. Tan, J. Liu, H. Li, D. Guan, J.-F. Jia, MnBi_2Te_4 —a good platform for topological quantum physics study, *Quantum Front.* 1 (2022) 19.
- [14] H.-K. Xu, F. Li, F.-C. Fei, L. Wang, Y.-S. Gu, D. Liu, Q.-Y. Yu, S.-S. Xue, K. Peng, B. Chen, et al., Visualization of rotational symmetry breaking electronic states in MnBi_2Te_4 and MnBi_4Te_7 , *Quantum Front.* 1 (2022) 5.
- [15] A. Zunger, Bridging the gap between density functional theory and quantum materials, *Nat. Comput. Sci.* 2 (2022) 529.
- [16] Y. Zhao, Q. Liu, Routes to realize the axion-insulator phase in $\text{MnBi}_2\text{Te}_4(\text{Bi}_2\text{Te}_3\text{n})$ family, *Appl. Phys. Lett.* 119 (2021) 060502.
- [17] H. Liu, H. Jiang, Q.-f. Sun, X.C. Xie, Dephasing effect on backscattering of helical surface states in 3d topological insulators, *Phys. Rev. Lett.* 113 (2014) 046805.
- [18] N.P. Armitage, E.J. Mele, A. Vishwanath, Weyl and dirac semimetals in three-dimensional solids, *Rev. Mod. Phys.* 90 (2018) 015001.
- [19] L.F. Mattheiss, Electronic structure of the 3d transition-metal monoxides. I. Energy-band results, *Phys. Rev. B* 5 (1972) 290.
- [20] L.F. Mattheiss, Electronic structure of the 3d transition-metal monoxides. II. Interpretation, *Phys. Rev. B* 5 (1972) 306.
- [21] F. Rivadulla, M. Banobre-Lopez, C.X. Quintela, A. Pineiro, V. Pardo, D. Baldomir, M. ArturoLopez-Quintela, J. Rivas, C.A. Ramos, H. Salva, J.-S. Zhou, J.B. Goodenough, Reduction of the bulk modulus at high pressure in *crn*, *Nat. Mater.* 8 (2009) 947.
- [22] I.A. Abrikosov, A.V. Ponomareva, P. Steneteg, S.A. Barannikova, B. Alling, Recent progress in simulations of the paramagnetic state of magnetic materials, *Curr. Opin. Solid State Mater. Sci.* 20 (2016) 85.
- [23] G. Trimarchi, Z. Wang, A. Zunger, Polymorphous band structure model of gapping in the antiferromagnet, *Phys. Rev. B* 97 (2018) 035107.
- [24] O.I. Malyi, A. Zunger, False metals, real insulators, and degenerate gapped metals, *Appl. Phys. Rev.* 7 (2020) 041310.
- [25] Y. Zhang, J. Furness, R. Zhang, Z. Wang, A. Zunger, J. Sun, Symmetry-breaking polymorphous descriptions for correlated materials without interelectronic *u*, *Phys. Rev. B* 102 (2020) 045112.
- [26] O.I. Malyi, G.M. Dalpian, X.-G. Zhao, Z. Wang, A. Zunger, Realization of predicted exotic materials: the burden of proof, *Mater. Today* 32 (2020) 35.
- [27] X.-Y. Chen, M.-Q. Long, Y.-P. Wang, Paramagnetic phases of two-dimensional magnetic materials, *Phys. Rev. B* 102 (2020) 214417.
- [28] K.F. Garrity, S. Chowdhury, F.M. Tavazza, Topological surface states of MnBi_2Te_4 at finite temperatures and at domain walls, *Phys. Rev. Mater.* 5 (2021) 024207.
- [29] G. Kresse, D. Joubert, From ultrasoft pseudopotentials to the projector augmented-wave method, *Phys. Rev. B* 59 (1999) 1758.
- [30] G. Kresse, J. Furthmüller, Efficient iterative schemes for ab initio total-energy calculations using a plane-wave basis set, *Phys. Rev. B* 54 (1996) 11169.
- [31] P.E. Blöchl, Projector augmented-wave method, *Phys. Rev. B* 50 (1994) 17953.
- [32] J.P. Perdew, K. Burke, M. Ernzerhof, Generalized gradient approximation made simple, *Phys. Rev. Lett.* 77 (1996) 3865.
- [33] S.L. Dudarev, G.A. Botton, S.Y. Savrasov, C.J. Humphreys, A.P. Sutton, Electron-energy-loss spectra and the structural stability of nickel oxide: an *l*sd α + *u* study, *Phys. Rev. B* 57 (1998) 1505.
- [34] S. Grimme, J. Antony, S. Ehrlich, H. Krieg, A consistent and accurate ab initio parametrization of density functional dispersion correction (dft-d) for the 94 elements *h*-pu, *J. Chem. Phys.* 132 (2010) 154104.
- [35] B. Kaduk, T. Kowalczyk, T. Van Voorhis, Constrained density functional theory, *Chem. Rev.* 112 (2012) 321.
- [36] T.B. Boykin, G. Klimeck, Practical application of zone-folding concepts in tight-binding calculations, *Phys. Rev. B* 71 (2005) 115215.
- [37] T.B. Boykin, N. Khariche, G. Klimeck, M. Korkusinski, Approximate bandstructures of semiconductor alloys from tight-binding supercell calculations, *J. Phys.: Condens. Matter* 19 (2007) 036203.
- [38] P.V.C. Medeiros, S. Stafström, J. Björk, Effects of extrinsic and intrinsic perturbations on the electronic structure of graphene: retaining an effective primitive cell band structure by band unfolding, *Phys. Rev. B* 89 (2014) 041407.
- [39] P.V.C. Medeiros, S.S. Tsirkin, S. Stafström, J. Björk, Unfolding spinor wave functions and expectation values of general operators: introducing the unfolding-density operator, *Phys. Rev. B* 91 (2015) 041116.
- [40] A. Zunger, S.-H. Wei, L.G. Ferreira, J.E. Bernard, Special quasirandom structures, *Phys. Rev. Lett.* 65 (1990) 353.

- [41] A. van de Walle, Multicomponent multisublattice alloys, nonconfigurational entropy and other additions to the alloy theoretic automated toolkit, *Calphad* 33 (2009) 266 (tools for Computational Thermodynamics).
- [42] A. van de Walle, P. Tiwary, M. de Jong, D. Olmsted, M. Asta, A. Dick, D. Shin, Y. Wang, L.-Q. Chen, Z.-K. Liu, Efficient stochastic generation of special quasirandom structures, *Calphad* 42 (2013) 13.
- [43] S. Nakatsuji, N. Kiyohara, T. Higo, Large anomalous hall effect in a non-collinear antiferromagnet at room temperature, *Nature* 527 (2015) 212.
- [44] C.-X. Liu, H. Zhang, B. Yan, X.-L. Qi, T. Frauenheim, X. Dai, Z. Fang, S.-C. Zhang, Oscillatory crossover from two-dimensional to three-dimensional topological insulators, *Phys. Rev. B* 81 (2010) 041307.
- [45] B. Dorado, P. Garcia, First-principles $dft + u$ modeling of actinide-based alloys: application to paramagnetic phases of uo_2 and (u,pu) mixed oxides, *Phys. Rev. B* 87 (2013) 195139.
- [46] L. Bergqvist, O. Eriksson, J. Kudrnovský, V. Drchal, A. Bergman, L. Nordström, I. Turek, Magnetic properties and disorder effects in diluted magnetic semiconductors, *Phys. Rev. B* 72 (2005) 195210.
- [47] H. Sun, B. Xia, Z. Chen, Y. Zhang, P. Liu, Q. Yao, H. Tang, Y. Zhao, H. Xu, Q. Liu, Rational design principles of the quantum anomalous Hall effect in superlattice-like magnetic topological insulators, *Phys. Rev. Lett.* 123 (2019) 096401.
- [48] S. Tian, S. Gao, S. Nie, Y. Qian, C. Gong, Y. Fu, H. Li, W. Fan, P. Zhang, T. Kondo, S. Shin, J. Adell, H. Fedderwitz, H. Ding, Z. Wang, T. Qian, H. Lei, Magnetic topological insulator $MnBi_6Te_{10}$ with a zero-field ferromagnetic state and gapped Dirac surface states, *Phys. Rev. B* 102 (2020) 035144.
- [49] I.I. Klimovskikh, M.M. Otrokov, D. Estyunin, S.V. Eremeev, S.O. Filnov, A. Koroleva, E. Shevchenko, V. Voroshnin, A.G. Rybkin, I.P. Rusinov, et al., Tunable 3d/2d magnetism in the (MnBi₂Te₄)(Bi₂Te₃)_n topological insulators family, *npj Quantum Mater.* 5 (2020) 54.
- [50] A. Shikin, N. Zaitsev, A. Tarasov, T. Makarova, D. Glazkova, D. Estyunin, I. Klimovskikh, Electronic and spin structure of topological surface states in MnBi₄Te₇ and MnBi₆Te₁₀ and their modification by an applied electric field, *JETP Lett.* 116 (2022) 556.
- [51] J. Li, R.-L. Chu, J.K. Jain, S.-Q. Shen, Topological Anderson insulator, *Phys. Rev. Lett.* 102 (2009) 136806.